



# ATMY ANALYTICAL LABS PVT.LTD.

(NABL/ISO 17025 Accredited Laboratory)

I-38, DLF Industrial Area, Phase-1, Faridabad (Haryana) INDIA  
Phone: +91-129-4019544, 6453754  
info@atmylabs.com, www.atmylabs.com

- Testing
- Research
- Innovation

## TEST REPORT

**Issued To :**  
PROFINE INDIA WINDOW TECHNOLOGY PVT LTD,  
PLOT NO. 727.SAVLI INDUSTRIAL AREA  
GIDC MANJUSASR,VADODRA  
  
GUJARAT-391775

**Sample / Material :**  
KOEMMERLING UPVC PROFILE

**DOI :** 01-May-2017  
**DOB:** 20-Apr-2017

Kind Attn. :

Client Ref. No. :

Report No.: 170420005-1003

RB11\RA000\IA60145

ID-1704200013


Page 1 of 2

### PHYSICAL TEST REPORT

TEST	UNIT	RESULT	TEST METHOD
Density	g/cm <sup>3</sup>	1.46	ASTM D792
Ball Impact Hardness	N/mm <sup>2</sup>	95	DIN ISO 239 T1
Tensile Strength	Mpa	50.1	ASTM D638
Elongation at Break	%	86	ASTM D638
Tensile Modulus	Mpa	2284	ASTM D638
Flexural Strength	Mpa	92	ASTM D 790
Flexural Modulus	Mpa	2602	ASTM D 790
Shore Hardness	Shore D	84	ASTM D2240
Izod notched Impact (at 23°C/Thickness 3.18 mm)	KJ/m <sup>2</sup>	30	DIN EN ISO 179
Charpy Impact Strength	---	No Break	DIN EN ISO 179

MSF 5.10.01

Analyst



Authorised Signatory

#### Terms & Conditions:

Test Certificate No. G-1003

1. Sample will not be retained more than one month for chemical and three month for mechanical unless specified instructed.
2. Sample analysis conducted on as received basis and followed by customer description, unless specified otherwise.
3. The laboratory will not be liable for sample destroy/ damage during testing, unless instructed otherwise.
4. Any Complaints matter about this report should be communicated in written, within 7 days of issue of this report.
5. The result listed refer on;y to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies.
6. Total liability of our laboratory is limited to the invoiced amount.
7. This report cannot be used as and evidence in a court of law without the written approval of the laboratory.